


BITUMINOUS CEMENT CONCRETE MIXTURES

Surface Designation Sieve Sizes	Percent Passing				
	SF	BC	BF	9.5mm SUPERPAVE	19.0mm SUPERPAVE
2 in.	—	100	—	—	—
1-1/2 in.	—	95-100	—	—	—
3/4 in.	—	60-90	85-98	100	100
1/2 in.	100	—	—	100	82-88
3/8 in.	75-98	35-55	50-75	75-90	60 MAX
No. 4	47-72	15-40	30-55	30-50	22-30
No. 8	34-56	10-29	18-40	20-30	14-20
No. 16	20-40	7-21	12-29	—	—
No. 200	1-9	2-6	2-9	8-13	9-11
A.C.	5.8-12.0	5.8-8.0	—	—	—

Note: Unless Otherwise Directed By The Engineer, The Contractors Laboratory Study Shall Be Submitted For Approval At Least Three Weeks Prior To Paving Operations. The Following Information Is Required.

- A. Mix Designation.
- B. Source And Percentage Of Aggregate, Asphalt Cement, Asphalt Release Agent, Anti-stripping And Any Other Additives.
- C. Combined Grading, Extracted Grading, If Used.
- D. Plant Where The HMA Mix Will Be Produced.
- E. Worksheets And Graphs Showing The Marshall Properties.
- F. Number Of Compaction Blows Per Face.
- G. Percent Passing No. 200 Sieve Removed By Dust Collecting System.
- H. Ratio Of Dust To Binder Material.
- I. Maximum Specific Gravity At The Target Asphalt Content.

APPROVAL	REVISED	TOWN OF EASTON AND EASTON UTILITIES STANDARD DETAILS BITUMINOUS CEMENT CONCRETE MIXTURES
 EU MANAGER OF ENGINEERING	AUG 1, 94	
	SEP 1, 98	
	AUG 1, 01	
	SEP 1, 02	
ISSUED: MAY 1, 1986		STANDARD NO. G-2.00